Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	CP-2019-01-11-50 **Date: 06-12-18**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division
Agency	:	Sri Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-12-18
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification . IS 4031 (Part 1,2 3,4,5, 6,11) 1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	04-12-18
Environmental Conditions during test	:	Temperature 26°C Humidity 72%

SLNo.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.85	–
2	Finess by Air permeablity method (m^2/kg,Min)	348.6	225m^2/kg, Min
3	Density (gm/cc)	3.15	–
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	135 minutes	Not less than 30 minutes
6	Final Setting time	245 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

AE-I
A.E.E
AE

Note:

The results pertain to the samples received and tested

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Date: 01-01-19

Lab ID	:	CP-2019-01-11-50
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-12-18
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification . IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	04-12-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

AE-1
A.E.E

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

(BBMP Ynk. Zn)

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2019-01-11-50** **Date: 06-12-18**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	03-12-18
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS. 383:2016 (Specification for Coarse and fine Aggregates) IS. 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	03-12-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80mm	0	0	0.0	100	100
2	40 mm	217	217	1.4	98.6	90-100
3	20 mm	7453	7670	51.1	48.9	30-70
4	10 mm	4266	11936	79.6	20.4	10-35
5	4.75 mm	2844	14780	98.5	1.5	0-5
6	Pan	220	15000	100.0	0	---

AE-1
A.E.E
AE

CIVIL PRO Sig..... Date..... BANGALORE

(BBMP YNK. ZII)

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2019-01-11-50** **Date: 06-12-18**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.8	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.7	
3	Specific Gravity	2.61	–
4	Bulk Density(Loose) (Kg/l)	1.41	–
5	Bulk Density(Compacted) (Kg/l)	1.47	–
6	Water Absorption(%)	0.23	–

Note:
The results pertain to the samples received and tested.
All information furnished by Customer Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

AE-1 A.E.E AE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

(BBMP Ynk. 2n)

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : CP-2019-01-11-50 Date: 05-12-18

Customer : Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.

Agency : Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.

Customer Reference : EE(YNK.D)E-PMT-19/WO/88/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 03-12-18

Sample Type/ Size : 20mm down size coarse aggregate

Reference to BIS codes : IS: 383:2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1,3,4) RA2011
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
IS 2386 Part 4: Mechanical Properties

Date of test : 03-12-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	225	225	4.5	95.5	90-100
3	10 mm	2845	3070	61.4	38.6	25-55
4	4.75 mm	1745	4815	96.3	3.7	0-10
5	Pan	185	5000	100	0	–

A.E.E

AE

CIVIL Pro Sig..... Date..... BANGALORE

(BBMP YNK. Zn)

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : CP-2019-01-11-50 Date: 05-12-18

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.1	
3	Specific Gravity	2.68	–
4	Bulk Density(Loose) (Kg/l)	1.43	–
5	Bulk Density(Compacted) (Kg/l)	1.49	–
6	Water Absorption(%)	0.23	–
7	Aggregate crushing Value(%)	22.9	Max 30% for Aggregates to be used in concrete for wearing Surface. In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.7	30% for Aggregates to be used in concrete for wearing Surface. 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-1
A.E.E
AE

FOR CIVIL Pro

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL Pro Sig Date BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID	:	CP-2019-01-11-50 **Date: 05-12-18**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	03-12-18
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 2016 (Specification for Coarse and fine Aggregates) IS 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	03-12-18
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

A.E.E

AE

CIVIL PRO Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES|

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2019-01-11-50** **Date: 05-12-18**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.45	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.2	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:
The results pertain to the samples received and tested
All information furnished by Customer Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2019-01-11-50** **Date: 11-12-18**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	10-12-18
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	10-12-18

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.392	514	652	20.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.615	526	672	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.886	542	668	20.0%	Satisfactory	Satisfactory

AE-1
A.E.E
AE

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	**CP-2019-01-11-50** **Date: 17-12-18**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-12-18
Sample Type /Size	:	Precast Cover Slab
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	12/12/2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.55	100.5	1.116	4482	82.6	18.4	17.1	21.4
2	Cover Slab-2	75.59	100.51	1.122	4487	82.2	18.3	17.0	21.3
3	Cover Slab-3	75.52	100.49	1.118	4478	81.4	18.2	16.9	21.1

AE-1
A.E.E

Note:
The results pertain to the samples received and tested
All information furnished by the Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID	:	CP-2019-01-11-50 **Date: 17-12-18**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	12-12-18
Sample Type /Size	:	Precast Cover Slab
Reference to BIS codes	:	IS 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	12/12 2018

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	165.51	200.48	2.116	21511	85.9	4.0	3.7	4.6
2	Cover Slab-2	165.49	200.52	2.122	21506	86.3	4.0	3.7	4.7
3	Cover Slab-3	165.50	200.51	2.118	21508	86.5	4.0	3.7	4.7

AE-1
A.E.E

Note:
1. The results pertain to the samples received and tested
2. Information furnished by the Customer Representative
3. Any correction in the report will make this report invalid
4. This report without prior written approval should not be reproduced or published in full or part
5. Samples will be disposed after 90 days from the date of issue of test certificate

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	: CP-2019-01-11-50	**Date: 26/12/2018**
Customer	: Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.	
Address	: Yelahanka Sub Division, BBMP, Bangalore.	
Project Name	: Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.	
Agency	: Sri.Harshith Raj R Noo/286, Doddaballapura, Bangalore.	
Customer's Reference	: EE(YNK.D)E-PMT-19/WO/88/2018-19	
Source of Sample	: Sample supplied by Agency	
Sample Condition	: Satisfactory	
Date of Receipt	: 21-12-18	
Customer ID	: Drain Bottom Slab Concrete	
Sample Type /Size	: 150X150X150 mm	
Sample grade/Age	: M20 / 7 Days Compressive Strength	
Reference to BIS codes	: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5	
Date of test	: 26/12/2018	

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	150.13 X 149.94 X 151.84	22510	8.362	427.3	19.0	18.5
2	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	151.43 X 151.21 X 149.51	22898	8.048	423.7	18.5	
3	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	150.29 X 151.13 X 149.82	22713	8.119	409.6	18.0	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-01-11-50 **Date: 16/01/2019**

Customer : Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division

Agency : Sri Harshith Raj R Noo:286, Doddaballapura, Bangalore.

Customer's Reference : EE(YNK DIE-PMT-19/WO/88/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-12-18

Customer ID : Dram Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/01/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	151.75 X 149.04 X 150.75	22617	8.992	537.8	23.8	23.1
2	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	151.07 X 151.09 X 150.29	22825	8.327	507.6	22.2	
3	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	150.66 X 150.76 X 151.00	22714	8.318	525.8	23.1	

Note:

The results pertain to the samples received and tested

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

AE-1

A.E.E

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2019-01-11-50** **Date: 26/12/2018**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri Harshith Raj R Noo'286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-12-18
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl 5
Date of test	:	26/12/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	150.33 X 151.07 X 150.07	22711	8.928	414.7	18.3	18.3
2	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	149.82 X 151.73 X 151.17	22732	8.754	418.8	18.4	
3	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	149.92 X 150.24 X 149.45	22524	8.199	412.6	18.3	

Note:
1. The results pertain to the samples received and tested.
2. All information furnished by Customer/Representative
3. Any correction in the report will make this report invalid
4. This report without prior written approval should not be reproduced or published in full or part.
5. Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig Date

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-01-11-50 **Date: 16/01/2019**

Customer : Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.

Agency : Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.

Customer's Reference : EE(YNK D)E-PMT-19/WO/88/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-12-18

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/01/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	150.97 X 150.81 X 149.05	22768	8.835	544.5	23.9	23.3
2	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	150.84 X 150.78 X 151.12	22744	8.075	517.8	22.8	
3	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	150.10 X 151.41 X 151.80	22726	8.963	524.4	23.1	

A.E.E

Note:
The results pertain to the samples received and tested
Information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

Page 1/1
****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	CP-2019-01-11-50 **Date: 16/01/2019**
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.
Agency	:	Sri.Harshith Raj R Noo:286, Doddaballapura, Bangalore.
Customer's Reference	:	EE(YNK.D)E-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-12-18
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS. 516 - 1959 Methods of Tests for Strength of Concrete Cl 5
Date of test	:	16/01/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm²)	Average Compressive Strength (N/mm²)
1	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	151.95 X 150.19 X 151.52	22820	8.520	538.3	23.6	23.2
2	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	149.56 X 150.58 X 150.02	22520	8.631	515.1	22.9	
3	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	149.36 X 149.12 X 151.19	22273	8.641	517.3	23.2	

Note:
The results pertain to the samples received and tested
Information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/01/2019

Lab ID	:	CP-2019-01-11-50
Customer	:	Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division
Agency	:	Sri Harshith Raj R Noo 286, Doddaballapura, Bangalore
Customer's Reference	:	EE(YNK DIV-PMT-19/WO/88/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-12-18
Customer ID	:	Drain Bottom Slab Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS 516 - 1959 Methods of Tests for Strength of Concrete Cl 5
Date of test	:	16/01/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	149.88 X 151.84 X 149.01	22759	8.378	542.4	23.8	23.1
2	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	149.54 X 150.29 X 149.40	22474	8.274	499.3	22.2	
3	Drain Bottom Slab Concrete	M20	19/12/2018	16/01/2019	151.30 X 150.91 X 150.84	22832	8.822	533.7	23.4	

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2019-01-11-50 Date: 26/12/2018

Customer : Assistant Executive Engineer,Yelahanka Sub Division, BBMP, Bangalore

Address : Yelahanka Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drain at Shushrusha Hospital Back Side in Ward No-01 of Yelahanka Sub Division.

Agency : Sri Harshith Raj R Noo:286, Doddaballapura, Bangalore.

Customer's Reference : EE(YNK DIE-PMT-19/WO/88/2018-19

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-12-18

Customer ID : Drain Bottom Slab Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/12/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	150.50 X 150.99 X 151.21	22723	8.934	413.5	18.2	18.5
2	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	150.96 X 149.00 X 149.75	22493	8.206	421.2	18.7	
3	Drain Bottom Slab Concrete	M20	19/12/2018	26/12/2018	151.10 X 150.18 X 151.08	22691	8.969	418.5	18.4	

AE-1

Note:
The results pertain to the samples received and tested
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

A.E.E

AE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

Page 1/1
****End of Report****